Thistle® essential selector guide



		Two-Coat levelling		One-Coat levelling & finishing	Finish Coat			
		Bonding Coat When the war was a second of the second of th	Hard Wall Water Person	Profice at Dirico at Management of the Control of t	Universal OneCoat	Photos MultiFinish Mustamana Managaman Paganah firms	Truster of Finish Board Finish Truster of Finish	Spray Finish Spray
0	Product	Thistle BondingCoat	Thistle HardWall	Thistle DriCoat	Thistle Universal OneCoat	Thistle MultiFinish	Thistle BoardFinish	Thistle SprayFinish
PRODUCT IN	Product description	For smooth or low suction backgrounds and surfaces treated with Thistle Bond-it	For medium to high suction backgrounds. Can be spray applied	Cement-based renovation product for re-plastering after a damp-proof course (DPC)	Suitable for many backgrounds. Can be applied by hand or mechanical plastering machine	Versatile skim plaster for finishing most plaster and plasterboard backgrounds	Designed for low to medium suction backgrounds especially plasterboards	Designed to work with worm pump spray machines or can also be hand applied. Ideal for low to medium suction backgrounds
PRODUCT INFO	Benefits of product	Ideal for repairs on multiple surfaces	Good coverage for large areas in renovations or traditional two-coat plastering	Takes the guesswork out for cement renovation plastering through consistent, reliable performance	Levels backgrounds like an undercoat, smooths to a quality finish	Provides a smooth, inert, high quality surface to internal walls and ceilings, and a durable base for the application of decorative finishes	Provides a smooth, inert, high quality surface to internal plasterboard walls and ceilings, and a durable base for the application of decorative finishes	Sprayed in a cross-hatching technique and flattened after 5 - 10 minutes. Trowel finished exactly as other Thistle skim. Once dry, the surface is ready for decorating with no need for any sanding or additional treatment
PREP	Preparation advice	Use Thistle Bond-it on any variant of moisture resistant plasterboard	Can be used on metal lathing when bridging columns and lintels. Should not be used with Thistle Bond-it or on smooth low suction blocks		Use Thistle Bond-it on any variant of moisture resistant plasterboard	Dampen dry undercoats first or where background suction is extremely high, use Thistle GypPrime. Use Thistle Bond-it on any variant of moisture resistant plasterboard	Use Thistle Bond-it on any variant of moisture resistant plasterboard	Use Thistle Bond-it on any variant of moisture resistant plasterboard
	Where to use - background surface							
	Aircrete blocks	-	Υ	Υ	Y	-	-	-
	Common bricks	-	Υ	Υ	Y		-	_
	Medium density blocks	Υ	Y	Y	Y		_	
	Dense blocks	Y	Y	Y	Y	- -	-	
	Engineered bricks with raked joints	Y	-	-	Υ	. 	-	-
NOI	Plasterboard and Glasroc F MultiBoard	Y		-	Υ	. 		
SUCT	Cast in situ and pre-cast concrete	Y		-	Y	-		-
	Painted/tiled surfaces	Y Y	- V	-	Y	Υ	-	
	Metal lathing	Y	Y	-	Y	- Y	-	
	Dry undercoats Damp undercoats					- <u> </u>		
	Plasterboard	_				- <u>'</u>	Y	
	Flat smooth concrete					· — · · · · · · · · · · · · · · · · · ·		Y
	Waterproof or cement-based undercoats	_	_	_	_	-	Y	Y
	Application					-	1	·
	Hand applied	Y	Y	Y		Y	Υ	Y
	Spray applied	-	Y	-		-	<u> </u>	Y
Z	Thickness applied - walls	11mm	11mm	11mm	13mm	2mm	2mm	
ATIO	Thickness applied - ceilings	8mm	8mm		10mm	2mm	2mm	2mm
ZLIC,	Coverage per bag at 11mm (undercoat)	2.75m²	3.0m²	3.25m ²	2.25m² (13mm)	- 	-	
APF	Coverage per bag at 2mm (finish)					10m²	10m²	
	Water requirement (litres per bag)	14	15	15	15	11.5	11.5	12
	Dry set weight at 11mm (undercoat)	11kg/m²	8.8kg/m ²	-	12.6kg/m² (13mm)	-	-	-
	Dry set weight at 2mm (finish)	-	-		-	2.7kg/m²	2.7kg/m²	2.7kg/m ²
SET	Minimum setting time*	200 mins	120 mins	24 hours**	90 mins	90 mins	90 mins	105 mins

Thistle Bond-it may be required for repairs on smooth/low suction such as dense blocks, MR boards, concretes and painted surfaces. Thistle GypPrime may be required for very high suction backgrounds such as undercoat plaster.

*Dependent on environmental conditions. **Allow to dry for a minimum of 24 hours before finishing.



