



CLIMAFLEX®

UK

MATERIAL	CLIMAFLEX® UK is a flexible insulating material made of foamed, closed-cell polyethylene.
LENGTH	2 m
THERMAL CONDUCTIVITY (EN ISO 8497)	0,036 W/mK at 0 °C 0,040 W/mK at 40 °C 0,053 W/mK at 90 °C
TEMPERATURE RANGE (EN 14707)	0 °C to +100 °C
FIRE PERFORMANCE (EN 13501-1)	Euroclass E
APPLICATION AREA	Heating and plumbing

ADVANTAGES

- Professional thermal insulation for energy savings of up to 80 %
- Improvement of the economic and ecological efficiency of the entire unit
- Sound absorbing insulation for acoustic comfort

See website for Declaration of performance: www.nmc-insulation.com



NMC (UK) LTD.

Tafarnaubach Industrial Estate · UK-NP22 3AA Tredegar, South Wales

Phone: +44 1495 713266 · Fax: +44 1495 713277

Email: enquiries@nmc-uk.com


www.nmc-insulation.com

nmc

PRODUCT RANGE

CLIMAFLEX®

UK



Type	Copper CU		Steel FE			Synthetics MSV & PEX	A mm	B mm	Pkg unit m
	NW DN	Outer Ø mm	NW DN	Outer Ø mm inch		Outer Ø mm			
10 x 9	8	10	6	10,2	1/8	-	10	9	460
15 x 9	10	15	8	13,5	1/4	-	15	9	380
22 x 9	20	22	15	21,3	1/2	20	22	9	250
28 x 9	25	28	20	26,9	3/4	25	28	9	190
35 x 9	32	35	25	33,7	1	32	35	9	150
42 x 9	40	42	32	42,4	1 1/4	40	42	9	110
48 x 9	-	-	40	48,3	1 1/2	-	48	9	90
54 x 9	50	54	-	54	-	50	54	9	70
60 x 9	-	-	50	60,3	2	-	60	9	66
76 x 9	65	76,1	65	76,1	2 1/2	-	76	9	48
15 x 13	10	15	8	13,5	1/4	-	15	13	256
18 x 13	15	18	10	17,2	3/8	16	18	13	220
22 x 13	20	22	15	21,3	1/2	20	22	13	180
28 x 13	25	28	20	26,9	3/4	25	28	13	140
35 x 13	32	35	25	33,7	1	32	35	13	120
42 x 13	40	42	32	42,4	1 1/4	40	42	13	90
48 x 13	-	-	40	48,3	1 1/2	-	48	13	70
54 x 13	50	54	-	54	-	50	54	13	66
60 x 13	-	-	50	60,3	2	-	60	13	48
76 x 13	65	76,1	65	76,1	2 1/2	-	76	13	40
15 x 19	10	15	8	13,5	1/4	-	15	19	134
22 x 19	20	22	15	21,3	1/2	20	22	19	108
28 x 19	25	28	20	26,9	3/4	25	28	19	96
15 x 25	10	15	8	13,5	1/4	-	15	25	100
22 x 25	20	22	15	21,3	1/2	20	22	25	80
28 x 25	25	28	20	26,9	3/4	25	25	25	66