



# Eurowall® +

Eurowall® + is a thermal insulation board. Its core consists of rigid polyisocyanurate PIR foam. The board is faced with a gas diffusion tight multilayer foil on both sides. Grid pattern on one side.



## Application(s)

Thermal insulation of full fill cavity walls

## Board

Description	Value	Unit	Tolerances	Standard
-------------	-------	------	------------	----------

### Dimensions

Length	1200	mm		
Width	460	mm		
Thickness range	75-140	mm	T2	EN 823
Density (core volume weight)	± 30	kg/m <sup>3</sup>		

### Appearance

Facing	Gas diffusion tight multilayer foil of which one side is reflective with grid pattern and the other side alkali resistant (mat grey).			
Edge finishing	Tongue and groove on four sides			

## Essential Characteristics

Description	Standard	EN code	Value	Unit
<b>Thermal conductivity (declared value)</b>				
All thicknesses	EN 13165	$\lambda_D$	0.022	W/m.K
<b>Fire behaviour</b>				
Reaction to fire (product as such)	EN 13501-1	Euroclasse	F	
<b>Emissivity*</b>				
		$\epsilon$	0.05	
<b>Water vapour diffusion coefficient (tabulated value)</b>				
	EN ISO 10456	$\mu$	50 - 100	

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user. An older version of this technical datasheet can be requested via [technicalservices@recticel.com](mailto:technicalservices@recticel.com) in case required.

### Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

[www.recticelinsulation.com](http://www.recticelinsulation.com)

FEEL  
GOOD  
INSIDE

**RECTICEL**  
insulation

## Insulation Values

Thickness (mm)	$\lambda_D$ -value (W/mK)	$R_D$ -value (m <sup>2</sup> K/W)
75	0.022	3.40
90	0.022	4.05
115	0.022	5.20
140	0.022	6.35

## Standards & Certificates

### Standards

Product standard	EN 13165:2012 + A2:2016
Production	ISO 9001:2015
Environmental management	ISO 14001:2015

### Certificates

BBA	02/3908
PEFC	100% PEFC - certificate number: CU-PEFC-867959

## Other / Miscellaneous

### Production plant

Stoke-on-Trent Enterprise Way, Meir Park – Stoke-On-Trent, ST3 7UN UK

### Handling / maintenance

Storage/handling Stock dry and protected from direct sunlight

\* Emissivity can only be taken into account in the thermal calculation of a wall when the insulation is installed in a non-ventilated cavity.

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user. An older version of this technical datasheet can be requested via [technicalservices@recticel.com](mailto:technicalservices@recticel.com) in case required.

### Recticel Insulation

Enterprise Way, Whittle Road, Meir Park, Stoke-on-Trent, Staffordshire, ST3 7UN, UK

[www.recticelinsulation.com](http://www.recticelinsulation.com)

FEEL  
GOOD  
INSIDE

